

# **TECHNICAL**

# **DATA SHEET**



---

**Sureweld 6013 Covered (Stick)  
Electrodes (SMAW) Mild Steel Electrodes**

Art. No. 984.8120001...

# TECHNICAL DATA SHEET

## Sureweld 6013 Mild Steel Electrodes

Art. No. 984.8120001...

### PRODUCT DESCRIPTION

Sureweld 6013 is an all-position electrode. The arc is very stable even when low-voltage open circuit transformers are used. The power of its arc allows depositing quick welds, medium penetration, and good appearance. Sureweld 6013 minimizes the risk of trapping the slag due to its special characteristics and mineral coating. Sureweld 6013 is used on a wide array of mild steel fabrication where ease of operation and good appearance is required. Sureweld 6013 is recommended for welding vehicle bodies, profiles, tanks, ducts chassis, freight cars, ornamental jobs and thin-sheet structures.

Classifications	AWS A5.1 : E6013
Approvals	CWB CSA W48 E4913
Industry	Industrial and General Fabrication Mobile Equipment Ship/Barge Building

Approvals are based on factory location. Please contact ESAB for more information.

Welding Current	DC+, DC- or AC
Coating Type	High titania

### Typical Tensile Properties

Condition	Yield Strength	Tensile Strength	Reduction in Area	Elongation
As Welded	482 MPa (70 ksi)	558 MPa (81 ksi)	55 %	27 %

### Typical Charpy V-Notch Properties

Condition	Testing Temperature	Impact Value
As Welded	0 °C (32 °F)	47 J (35 ft-lb)

### Typical Weld Metal Analysis %

C	Mn	Si
0.10	0.60	0.50

**Deposition Data**

<b>Diameter</b>	<b>Current</b>	<b>Deposition Rate</b>	<b>Deposition Efficiency %</b>
3.2 mm (1/8 in.)	120-135 A	1 kg/h (2.1 lb/h)	73 %
2.4 mm (3/32 in.)	60-90 A	0.7 kg/h (1.6 lb/h)	73 %
4.0 mm (5/32 in.)	145-190 A	1.2 kg/h (2.6 lb/h)	75 %
4.0 mm (5/32 in.)	145-190 A	1.45 kg/h (3 lb/h)	74 %

# TECHNICAL DATA SHEET

## Sureweld 6013 Covered (Stick) Electrodes (SMAW) Mild Steel Electrodes

Art. No. 984.8120001...

2021

**Würth Canada Limited**

345 Hanlon Creek Boulevard

Guelph, Ontario, Canada

N1C 0A1

T (905) 564-6225

F (905) 564-3671

For general inquiries, please contact: [info@wurth.ca](mailto:info@wurth.ca)

Printed in Canada. All rights reserved. May not be reproduced, in part or in whole, without prior consent.

Copyright © 2021 Würth Canada Limited/Limitée. All Rights Reserved.

Please note that while Würth Canada has made diligent efforts to illustrate and describe the products shown in its catalogues and online media, these illustrations and descriptions however, are for the sole purpose of identification and do not express nor imply a warranty or condition that the products shown are merchantable, fit for a particular purpose, nor does it guarantee that the products will necessarily conform to the illustrations and descriptions.

