

TECHNICAL DATA SHEET



Sureweld 7014 Covered (Stick) Electrodes (SMAW) Mild Steel Electrodes

Art. No. 984.812000...



TECHNICAL DATA SHEET

Sureweld 7014 Mild Steel Electrodes

Art. No. 984.812000...

PRODUCT DESCRIPTION

Sureweld 7014 is an iron powder coated electrode permitting the use of higher welding currents while improving the deposition rate. High speeds and high heats can be used without undercut. Slag removal is excellent. Sureweld 7014 is widely used for welding mild steels such as ASTM A-36, A-113, A-283, A-284, A-285, A-306, A-515 and A-516. Typical applications include construction equipment, metal fixtures, automotive parts, barges and farm machinery.

Classifications	AWS A5.1 : E7014
Industry	Industrial and General Fabrication Mobile Equipment Ship/Barge Building

Approvals are based on factory location. Please contact ESAB for more information.

Welding Current	DC+, DC- or AC
Coating Type	Iron powder, titania

Typical Tensile Properties

Condition	Yield Strength	Tensile Strength	Reduction in Area	Elongation
As Welded	420 MPa (61 ksi)	490 MPa (71 ksi)	64 %	28 %

Typical Weld Metal Analysis %

c	Mn	Si	S	Ρ
0.04	0.30	0.14	0.02	0.02



TECHNICAL DATA SHEET

Sureweld 7014 Mild Steel Electrodes

Art. No. 984.812000...

Deposition Data

Diameter	Current	Deposition Rate	Deposition Efficiency %
3.2 mm (1/8 in.)	100-150 A	1.1 kg/h (2.4 lb/h)	63.9 %
3.2 mm (1/8 in.)	100-150 A	1.4 kg/h (3.1 lb/h)	61.1 %
2.4 mm (3/32 in.)	70-100 A	0.9 kg/h (2 lb/h)	60 %
4.0 mm (5/32 in.)	160-200 A	1.4 kg/h (3 lb/h)	71.9 %
4.0 mm (5/32 in.)	160-200 A	1.7 kg/h (3.7 lb/h)	67 %



TECHNICAL DATA SHEET

Sureweld 7014 Covered (Stick) Electrodes (SMAW) Mild Steel Electrodes

Art. No. 984.812000...

2021

Würth Canada Limited 345 Hanlon Creek Boulevard Guelph, Ontario, Canada N1C 0A1 T (905) 564-6225 F (905) 564-3671 For general inquiries, please contact: *info@wurth.ca* Printed in Canada. All rights reserved. May not be reproduced, in part or in whole, without prior consent.

Copyright © 2021 Würth Canada Limited/Limitée. All Rights Reserved. Please note that while Würth Canada has made diligent efforts to illustrate and describe the products shown in its catalogues and online media, these illustrations and descriptions however, are for the sole purpose of identification and do not express nor imply a warranty or condition that the products shown are merchantable, fit for a particular purpose, nor does it guarantee that the products will necessarily conform to the illustrations and descriptions.

