



DANGER Extremely flammable aerosol. Pressurised container: May burst if heated. Causes skin irritation. May cause drowsiness or dizziness. Suspected of damaging the unborn child. May cause damage to organs (Central nervous system) through prolonged or repeated exposure. **Prevention:** Obtain special instructions before use. Do not handle until all safety precautions have been read and understood. Keep away from heat, hot surfaces, sparks, open flames and other ignition sources. No smoking. Do not spray on an open flame or other ignition source. Do not pierce or burn, even after use. Do not breathe spray. Wash skin thoroughly after handling. Use only outdoors or in a well-ventilated area. Wear protective gloves, protective clothing, eye protection and face protection. **Response:** IF ON SKIN: Wash with plenty of water. If skin irritation occurs: Get medical attention. IF INHALED: Remove person to fresh air and keep comfortable for breathing. Call a doctor if you feel unwell. IF exposed or concerned: Get medical attention. Take off contaminated clothing and wash it before reuse. **Storage:** Store locked up. Protect from sunlight. Do not expose to temperatures exceeding 50 °C (122 °F). **Disposal:** Dispose of contents and container to an approved waste disposal plant.



See the **SDS** for more info at/Voir la **FDS** pour plus d'info au: wurth.ca or call/ou appelez: **1-800-263-5002**

Imported by/Importé par:

Wurth Canada Limited/Limitée

345 Hanlon Creek Blvd, Guelph, ON, N1C 0A1

DANGER Aérosol extrêmement inflammable. Récipient sous pression: peut éclater sous l'effet de la chaleur. Provoque une irritation cutanée. Peut provoquer somnolence ou des vertiges. Susceptible de nuire au fœtus. Risque présumé d'effets graves pour les organes (Système nerveux central) à la suite d'expositions répétées ou d'une exposition prolongée. **Prévention:** Se procurer les instructions avant utilisation. Ne pas manipuler avant d'avoir lu et compris toutes les précautions de sécurité. Tenir à l'écart de la chaleur, des surfaces chaudes, des étincelles, des flammes nues et de toute autre source d'ignition. Ne pas fumer. Ne pas vaporiser sur une flamme nue ou sur toute autre source d'ignition. Ne pas perforeur ni brûler, même après usage. Ne pas respirer les aérosols. Se laver la peau soigneusement après manipulation. Utiliser seulement en plein air ou dans un endroit bien ventilé. Porter des gants de protection, des vêtements de protection, un équipement de protection des yeux et du visage. **Intervention:** EN CAS DE CONTACT AVEC LA PEAU: Laver abondamment à l'eau. En cas d'irritation cutanée: Consulter un médecin. EN CAS D'INHALATION: Transporter la personne à l'extérieur et la maintenir dans une position où elle peut confortablement respirer. Appeler un médecin en cas de malaise. En cas d'exposition prouvée ou suspectée: Consulter un médecin. Enlever les vêtements contaminés et les laver avant réutilisation. **Entreposage:** Garder sous clef. Protéger du rayonnement solaire. Ne pas exposer à une température supérieure à 50 °C (122 °F). **Élimination:** Éliminer le contenu et le récipient dans une installation d'élimination des déchets agréée.

HIGH SOLIDS ENAMEL PAINT

PEINTURE-ÉMAIL GARNISSANTE



Net content/Contenu net:

440 g (15.5 oz)

EN HIGH SOLIDS ENAMEL PAINT

Features: A superior industrial spray paint formulated for maintenance operations where maximum performance is required. This high solids paint does not run or sag, and gives twice the coverage of conventional spray paints. Quick dry formula. Resists oil, gas and sun fading. Heat resistant up to 149 °C (300 °F).

Uses: Ideal for a wide variety of industrial, construction or marine applications on most types of metal and wood.

Directions: Surface must be clean, dry and free of rust. For maximum protection, the use of a primer is recommended. For best results, use when the ambient and pressurized container temperatures are between 10 and 32 °C (50 to 90 °F) and humidity is below 85%. Protect surrounding areas from overspray. Shake for at least one minute after the mixing ball dislodges and becomes audible; shake occasionally during use. Spray surface with steady, even strokes at a distance of 20 to 25 cm (8 to 10 in). Several light coats give a better finish than one heavy coat. **Dry to touch:** After ≈ 10 min. **Tack free:** ≈ 30 min. **Recoat:** Within 1 h or after 48 h.

Cautions: Test a small hidden area for compatibility before painting and recoating. Dry times vary with temperature, humidity, and coat thickness. If the nozzle clogs, pull it off with a twisting motion and rinse it in a solvent such as mineral spirits. Do not insert any object into the container opening. Reinsert the nozzle with a light twist with the pressurized container oriented away from the user. Empty the nozzle after each use by turning the container upside down and spraying briefly.

This information is based on our experience. Preliminary tests are advised before use.

FR PEINTURE-ÉMAIL GARNISSANTE

Caractéristiques: Une peinture industrielle supérieure en aérosol formulée pour les opérations d'entretien où des performances maximales sont requises. Cette peinture à haute teneur en matières solides ne s'écoule et ne s'affaisse pas et donne deux fois plus de couverture que les peintures conventionnelles. Formule à séchage rapide. Résiste à l'huile, au pétrole et à la décoloration du soleil. Résistant à la chaleur jusqu'à 149 °C (300 °F).

Utilisations: Idéal pour une grande variété d'applications industrielles, de construction ou marines sur la plupart des types de métal et de bois.

Mode d'emploi: La surface doit être propre, sèche et exempte de rouille. Pour une protection maximale, l'utilisation d'un apprêt est recommandée. Pour de meilleurs résultats, utiliser lorsque les températures ambiante et du contenant pressurisé sont entre 10 et 32 °C (50 et 90 °F) et que l'humidité est inférieure à 85%. Protéger les zones environnantes contre les excès de pulvérisation. Agiter pendant au moins une minute après que la bille de mélange se déloge et devient audible; agiter occasionnellement pendant l'utilisation. Pulvériser la surface avec des coups réguliers à une distance de 20 à 25 cm (8 à 10 po). Plusieurs couches légères donnent une meilleure finition. **Sec au toucher:** Après ≈ 10 min.

Sec hors-poisie: ≈ 30 min. **Recouvrable:** En 1 h ou après 48 h.

Avertissements: Testez la compatibilité sur une petite zone cachée avant de peindre et de recouvrir. Les temps de séchage varient avec la température, l'humidité et l'épaisseur de la couche. Si la buse se bouche, la retirer avec un mouvement de torsion et la rincer dans un solvant tel que l'essence minérale. Ne pas insérer un objet dans l'ouverture du récipient. Réinsérer la buse avec une torsion légère avec le récipient pressurisé orienté loin de l'utilisateur. Vider la buse après chaque utilisation en tournant le récipient à l'envers et en vaporisant brièvement. Cette information est basée sur notre expérience. Des tests préalables sont avisés avant l'utilisation.

**Not for retail sale/
Pas pour la vente au détail**

Made in USA/Fabriqué aux États-Unis

Art. 0892150027 083

Art. 892.150027 083

