

EUROCLEAR PRO 2:1 URETHANE CLEARCOAT



A European style, low VOC, medium solid 2:1 mix urethane clearcoat formulation

Features:

- Versatility with three activators: Fast, Standard, Slow
- High gloss, fast dry finish with superior depth of image that will perform with water-based and solvent-based basecoat systems
- Easy to spray, polish and buff.

Suitable surfaces:

- Automotive refinish basecoats (water and solvent based)
- Automotive refinish single stage
- Existing finishes that have been sanded and cleaned

Note: Clearcoat should not be applied over acrylic lacquers or existing finishes which have not been sanded.

Advantages:

- Easy application, polishing and buffing
- Durable, high gloss
- Superior depth of image
- Fast drying

Product	Content	Art. No.	P. Qty.
2:1 Clearcoat	5 L	5866.200106	1
Slow activator	2.5 L	5866.400110	
Standard activator		5866.400111	
Fast activator		5866.400112	

Dry and Flash Time

	Slow	Standard	Fast
Flash Time	15-20 min	10-15 min	5-10 min
Tack Free	1 hr	45 min	20 min
To Sand	6-8 hrs	3-6 hrs	3-6 hrs
To Buff	6-8 hrs	3-6 hrs	3-6 hrs
To Deliver	6-8 hrs	3-6 hrs	3-6 hrs

Pot Life

Activator	Time
Slow	1.5 hrs
Standard	35-45 min
Fast	25-35 min

Note: Pot Life will shorten as temperatures increase. Not recommended for use in temperatures below 16°C.

Mix Ratio: 2:1 (Clearcoat 2 parts : Activator 1 part)

Stir thoroughly between each addition and strain before spraying material

Application:

1. Allow the final coat of basecoat to dry in accordance with manufacturer's directions.
2. Use a tack cloth to remove any surface contaminates that may have settled on the basecoat.
3. Apply two full wet coats to a maximum of 6 mils wet, allowing 10 to 15 minutes flash time between coats or as conditions dictate.

Notes: DO NOT apply over non catalyzed acrylic or synthetic enamels or acrylic lacquer finishes.

- It is important to test the compatibility of this product with your paint system. This product is not recommended for use in temperatures below 16°C. The use below these temperatures will affect dry times, performance and finish. Always keep containers closed to prevent moisture contamination.

Force Drying:

- Purge Time: 40 min
- Bake Time: at 140°F: 40 min
- Allow the final coat to flash for 20 minutes before baking. May be wet sanded and buffed after 1 hour of cool down time. Baking will increase gloss.

Repairing and Recoating:

- May be recoated after 8 hours of dry time or upon cool down after force drying. After 24 hours, Euroclear must be sanded with 1200 to 1500 grit before recoating.

Many factors beyond Würth's control and uniquely within user's knowledge and control can affect the use and performance of a Würth product in a particular application. Given the variety of factors that can affect the use and performance of a Würth product, user is solely responsible for evaluating the Würth product and determining whether it is fit for a particular purpose and suitable for user's method of application. Würth makes no warranty, either expressed or implied, and specifically excludes any implied warranties or conditions of quality, whether of merchantability, fitness or otherwise. On any claim, irrespective of the legal theory invoked, Würth's total liability shall not exceed the purchase price of the product. In no event shall Würth be liable for any damages of any type, or for loss.